

ULTIMA LIGHT

Customer Service USA 1800 862 9022
www.panelrey.com

Manufacturer

Planta PANEL REY
Carretera Monterrey-Monclova km 11.5
El Carmen, NL. CP. 66560
Serafín Peña # 938 Sur C.P. 64000
Monterrey, Nuevo León. Phone: 1 800 862 9022

Description

Panel Rey Ultima Light® is ideal to achieve smooth surface and is easy to sand to accomplish desired level of finishing. It is 20% lighter than traditional compounds, and has been produced to prevent cracks and reduce the percentage of shrinkage.

Basic uses

This product is designed for treating fasteners, plastic, metal accessories and gypsum boards joints in walls and ceilings, as well as for applying finishing textures.

Advantages

- Lighter than traditional compounds
- Smooth and easy to sand for better finishing
- Low shrinkage and cracking

Limitations

- Drying time may vary depending on the weather conditions.
- All surfaces must be dry, clean and free of grease or dust.
- Keep proper ventilation in the work area to eliminate excess moisture.
- Do not add more than 2% (by weight of product) of water because it may cause cracking and bonding problems. Re-mix uniformly after thinning.
- Do not mix with other products.

Storage

Joint compounds and finishing products have a nine-month warranty, effective from the date of manufacture, and when stored under normal conditions, and in protected places. Do not stack more than two pallets high.

Caution

Avoid dust from damp sanding. Use a mask and safety goggles. Dust resulting from sanding may irritate eyes, nose or throat. In the event of visual contact, thoroughly wash with water for 15 minutes until all particles are removed. If irritation persists, get medical attention. Do not ingest this product. KEEP OUT OF THE REACH OF CHILDREN. For more safety information refer to the SDS on Panel Rey's website.

Greenguard Certified

Product certified for low chemical emissions.
UL.COM/GG UL 2818

Preparation

Mix contents uniformly without adding water for covering fasteners and corner beads. For taping and finishing joints, thin as necessary by adding clean water especially for use in mechanicals tools.
This product is manufactured to meet requirements established in ASTM-C475.

Composition

Latex type formulation with limestone filler and additives.
Contains No Asbestos.

General Application

FIRST COAT COVERING JOINTS, ACCESORIES AND FASTENERS

Apply Ultima Light compound over joints and place a joint tape to increase flexibility, remove any excess of compound over the joint tape.

Apply Ultima Light compound over accessories and fasteners, remove any excess of compound.

SECOND COAT

After the first coat of Ultima Light compound is completely dry apply a second coat over joints, accessories and fasteners to equate surface.

FINISHING

After the second coat is completely dry, softly sand over joints, accessories and fasteners, removing any excess of dry compound to leave a smooth surface.

TECHNICAL REFERENCES

- ASTM C840: Standard Specification for Application and Finishing of Gypsum Board.
- GA-214: Gypsum Association publication "Levels of Gypsum Board Finish."
- GA-216: Gypsum Association publication "Recommended Specifications for the Application and Finishing of Gypsum Board."

COVERAGE	7.3 ft ² /lb (1.5m ² /kg)	
Carton	38 lb (17.4 kg)	3.5 gal (13.2 L)
Pail	49 lb (22.4 kg)	4.5 gal (17 L)



SUBMITTAL APPROVALS

Job Name _____
Contractor _____
Date _____

* For complete warranty details, visit www.panelrey.com

Stamps/Signatures